



AF/1700
PATENT
\$

Case Docket No. IIDAP10.001AUS
Date: December 6, 2002
Page 1

In re application of : Miyoshi, et al.
App. No. : 09/844,155
Filed : April 27, 2001
For : COPPER ALLOY SUITABLE
FOR AN IC LEAD PIN FOR A
PIN GRID ARRAY PROVIDED
ON A PLASTIC SUBSTRATE
Examiner : Ip, Sikyin
Art Unit : 1742

) I hereby certify that this correspondence and all
) marked attachments are being deposited with the
) United States Postal Service as first class mail in an
) envelope addressed to: United States Patent and
) Trademark Office, P.O. Box 2327, Arlington, VA
) 22202, on
) 12/6/02
) (Date)
)
) Thomas R. Arno, Reg. No. 40,490

UNITED STATES PATENT AND TRADEMARK OFFICE BOX AF
P.O. Box 2327
Arlington, VA 22202

RECEIVED
DEC 12 2002
TC 1700

Sir:

Transmitted herewith is an Amendment after Final in the above-identified application.

(X) An extension of time to respond for 1 month is hereby requested.

Time Extension Fee:

(X) one month (\$110 large entity)

(X) Return prepaid postcard.


(X) A check in the amount of \$110 is enclosed.

(X) Please charge any additional fees, including any fees for additional extension of time, or credit overpayment to Deposit Account No. 11-1410.

(X) Please use Customer No. 20,995 for the correspondence address.

12/11/2002 SDENBOB1 00000049 09844155
01 FC:1251 110.00 OP

Thomas R. Arno
Registration No. 40,490
Attorney of Record
Customer No. 20,995
(619) 235-8550



IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Applicant : Miyoshi, et al.) Group Art Unit 1742
Appl. No. : 09/844,155)
Filed : April 27, 2001)
For : COPPER ALLOY SUITABLE FOR AN)
IC LEAD PIN FOR A PIN GRID)
ARRAY PROVIDED ON A PLASTIC)
SUBSTRATE)
Examiner : Ip, Sikyin)

DEC 12 2002
TC 1700
10/C
12/13/02

AMENDMENT AFTER FINAL

United States Patent and Trademark Office
P.O. Box 2327
Arlington, VA 22202

Dear Sir:

In response to the Office Action dated August 7, 2002, please amend the above captioned patent application as set forth below.

IN THE CLAIMS:

Please amend Claims 1-4 as follows:

1. (Amended) A copper alloy suitable for an IC lead pin for a pin grid array provided on a plastic substrate, wherein the copper alloy is selected from the group consisting of:

a copper alloy consisting of 0.05 to 0.5 wt% of Zn and 0.05 to 0.5 wt% of Mg, with the balance being made of unavoidable impurities and Cu;

a copper alloy consisting of 0.1 to 1.0 wt% of Sn, with the balance being made of unavoidable impurities and Cu; and

a copper alloy consisting of 0.1 to 1.0 wt% of Sn and 0.1 to 0.6 wt% of Ag, with the balance being made of unavoidable impurities and Cu;

wherein the copper alloy has conductivity of 50% IACS or more, and tensile stress of 400 MPa or more but 650 MPa or less.